


Technical Data Sheet

URJA STRIPP-COAT



TYPICAL PROPERTIES

Appearance	Green/Red/Blue/Saffron
Coverage	100 sq.ft/ liters
Dry Filmthickness (per coat)	50 Micron
PH	7
Non-Volatile content	55-60 Percent
Solids by content	40-45b Percent
Viscosity	150-160 seconds at room temperature by Ford Cup #4
Density	1.2
Dry to touch time	20 min.
Dry to re-coat time	1 hour
VOC Actual	1 to 2 Percent

TEST DATA

Humidity chamber (ASTM D-1748) 500 hr  
Outdoor Exposure (2 coats) 1500 + hr

PACKAGING AND STORAGE

URJA-Stripp-Coats available in 20, 30, 50 Liters plastic drums.  
URJA-Stripp-Coat should be stored at temperature below 30°C and do not expose to sunlight.  
Shelf life is up to 12 months.



URJA SEALANTS PVT. LTD.

P 230, MAYUR TRADE CENTRE, OLD PUNE-MUMBAI ROAD, CHINCHWAD, PUNE 411 019.  
PH NO.: +91 20 27472234 / 32662039 / 27442234 TELEFAX: +91 20 27472234.  
E-mail: urjasealant@gmail.com Web: www.urjasealantsandchemicals



PEELABLE-COATING

URJA  
SEALANTS PVT. LTD.

P 230, MAYUR TRADE CENTRE, OLD PUNE-MUMBAI ROAD, CHINCHWAD, PUNE 411 019.  
PH NO.: +91 20 27472234 / 32662039 / 27442234 TELEFAX: +91 20 27472234.  
E-mail: urjasealant@gmail.com Web: www.urjasealantsandchemicals