

UNISIL - NK- 70

TYPICAL PHYSIOCHEMICAL PROPERTIES

PROPERTY	UNIT	UNISIL NK-70
Appearance	-	Snow white free flowing powder
Behaviour towards water	-	Hydrophilic
Moisture (105°C) ²	%	5 ± 1.5
Ignition Loss (900° C for 2 hrs) ³	% max	6
Surface Area (BET) ⁴	m ² /gm	100-115
Average Particle size – Primary ⁹ Secondary ⁹	nm	10-12
	µm	14-16
Water Absorption	%	230-260
Oil Absorption	%	225-255
Bulk Density ^{1,5}	gm/cc	0.12 - 0.16
pH (2% acq. solution) ⁶	---	6.2 - 7.0
Residue on 300 mesh ⁷	% max	1.0
Specific Gravity	---	2 ± 0.02
Refractive Index	---	1.46
SiO ₂ ⁸	%	98-99
Al ₂ O ₃ ⁸	% max	0.2
R ₂ O ₃ ⁸	% max	0.3
Fe as Fe ₂ O ₃ ⁸	% max	0.3
Storage Stability	Practically unlimited under favorable transport/storage condition.	
Packing	kgs/bag	25

Doc. No.: SIL-17

Issue No.: 03

Issue Date: 17/11/2015

Replaces: All Previous Issues

This information and our technical advice-whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sales and Delivery.

Correspondence Address :

111/230, Harsh Nagar
KANPUR - 208 012. (INDIA)
Ph. :0512-2555292
Website: www.mlagroup.com
Email: info@mlagroup.com

1) At the time of packing 2) By IR Moisture Balance 3) IS:12076-1986(A-4) 4) Determined on coulter SA 3100 Surface Area Analyzer (by Nitrogen adsorption BET method) 5) IS: 7589-1974 (A-8) 6) IS: 12076-1986(A-2) 7) IS: 2850-1983 (A-5.1) 8) Based on material ignited at 900°C for 1 hour. 9) Determined on SEM-XRD machine.

CERTIFICATIONS

