

HANWHA

Ethylene Vinylacetate Copolymer

1316

Foam Molding Grade

MELT INDEX 1.8
VA CONTENT 18.0

HANWHA EVA 1316 is manufactured by Dow autoclave high pressure process and designed for variety of foam molding application such as shoes and sandals etc.. EVA 1316 is well known for its excellent processability and high quality assurance.

▣ Outstanding Properties

Excellent Foam Molding Property
Very Good Mechanical Properties
Excellent Loading Property of Various Fillers
Good Elastic Property of Sponge

▣ Processing Conditions

Kneader : 80 ~ 100°C
Roll Mill : 90°C

▣ Additives

No Additives

▣ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	1.8
VA Content	wt%	HCC Method ⁽³⁾	18.0
Density	g/cm ³	ASTM D1505	0.940
Vicat Softening Point	°C	ASTM D1525	59
Melting Point	°C	ASTM D3417	85
Tensile Strength at Break	kg/cm ²	ASTM D638	135
Elongation at Break	%	ASTM D638	850
Brittleness Temperature, F ₀	°C	ASTM D746	<-76
Hardness	Shore A/D	ASTM D2240	90/36

1. These are typical properties : not to be construed as specification.
2. The value for this property is dependent on part geometry and fabrication conditions.
3. Elemental Analyzer and FT-IR



HANWHA CHEMICAL CORPORATION

Hanwha B/D, 1 Changgyo-dong, Chung-ku, Seoul, Korea. Tel : 82-2-729-1282 Fax : 82-2-729-2998