



Zincolet - 42

Processing Additives

Composition	:	Blend of Fatty Acids, Fatty Acid Esters, Fatty Soaps and Fatty amide.
Specification	:	Appearance:Creamish color flakes.Drop Point: $90 \pm 5 \circ C$ Ash content (2hrs,@850°C): 1.0% Max
Dosage	:	3 - 5 phr.
	Su inj Fo	itable for Continuous vulcanization as well as for ection moulding. r all rubbers including moulded and extruded goods d footwear.
Packing	:	25 kg Polylinedpolywoven bag / Polylined paper bag.
Storage stability	:	Up to 2 years in normal storage conditions.
Approvals	:	REACH/SVHC
Handling		Consult material safety data sheet (MSDS) for additional handling information for Zincolet - 42.

PUKHRAJ ADDITIVES LLP

An ISO 9001:2008 Certified Company 5B, 5tth Floor, Diamond House, Plot No. 515, Behind National College, TPS III, 35th Road, Bandra (W), Mumbai, Maharashtra - 400 050 (INDIA). ☎Tel: +91-9833538089/+91-22-26494911/26494912/26494913

Email: info@pukhrajzincolet.com Visit us at: www.pukhrajzincolet.com

Information provided herein is based upon tests believed to be reliable. We have no control over the manner in which others may use this information, it does not guarantee the results to be obtained. The company assumes no obligation or liability for the information in this document. No warranties are given, all implied warranties of merchantability or fitness for a particular purpose are expressly excluded.