

ATTAPULGITE CLAY API SECTION 12



packing as per buyers requirement or in :

1 MTS jumbo bags

50 kgs new hdpe bags

40 kgs new hdpe bags

25 kgs new hdpe bags

Lumps loose

Lumps in bags

Physical Parameter AS per API

TESTING PARAMETER	REQUIRED	RESULT
Viscometer dial reading at 600 rpm 20 gram in 350 saturated salt solution (40-45 % Salt in deionized water for 20 min in HBM	30	>31
Residue greater than 75 microns Wt %	8 max	3
Moisture in Wt % at the time of bagging	16MAX	13