



VISTA

VISTA FLOOR TOP-M METALLIC SURFACE HARDENING COMPOUND

DESCRIPTION:

Vista Floor Top-M – is a graded metallic formulation that homogeneously gels with cement to form extra tough concrete floors.

USES :

On pavement and floor where hardness, anti-skid, abrasion and impact resistance properties are required, e.g. foot path, godown and ware houses where metal wheeled carts ply, runway, heavy traffic lanes, service station, parking lots, skating rinks, playing courts, garages and workshops, foundries, steel casting units, etc.

ADVANTAGE :

- High Impact resistance.
- High abrasion resistance.
- Low mechanical wear and tear, long durability.
- Anti-skid, even when wet.
- Economical
- Excellent finish
- Easy to apply

APPLICATIONS :

The substrate concrete on which Vista Floor Top-M is to be broadcasted, should be at least M-20 grade concrete, prepared with a low water-cement ratio, preferably admixed with a water reducing plasticizer like Vista Superplast .After the bleed water has evaporated a dry mix of 1 part Vista Floor Top -M and 4 parts of cement has to be sprinkled and finished with steel trowel. Broadcasting is to be done by hand and immediately the floor top should be smoothed either by hand trowel or mechanically. Over trowelling should be strictly avoided. Finishing should be done competently and power float can be used, if desired. Curing to be done as per standard practice for 28 days. The floor can be open to light vehicular traffic from 7 days onward and full use after 28 days. The thickness of the heavy duty flooring varies from 10 to 12 mm to be laid over a substrate of 38 to 40 mm.



VISTA

PROPERTIES:

Aspect	Metallic Grey Granule	
Moh's Hardness	91 (Steel score)	
Water Absorption	5 to 6%	
Abrasion Resistance	1.5 (mean)	
Coverage	Light duty floor	2 to 3Kg per M ²
	Heavy Duty floor	5 to 7 Kg per M ²

SHELF LIFE:

18 months from the date of manufacture.

PACKING:

30 Kg bags should be stored in a dry place

HANDLING PRECAUTION:

Vista Floor Top-M is non –Toxic and Ingestion is to be avoided. If contact with eyes occurs, wash well immediately with water and seek medical advice.

NOTE :

- The contents of the technical data sheet are for general information and guideline only. Results shown here are generated from our laboratory or from our site experiences. This behavior may change as per prevailing condition at the time of application.
- VISTA maintains a team of technical trained professional to provide full support in regards to any of our products.

Manufactured & marketed by

VISTA CHEMTECH PVT. LTD.

(An ISO 9001 Certified Co.)

A SURANA GROUP OF INDUSTRIES

Corporate Office :

7/1B, Grant Lane, Kolkata – 700 012, (INDIA)

T : +91 33 2237 9394 / 2236 0469 / 2215 5513

F : +91 33 2237 9394

Works :

PO - Jalabishwanathpur, Amta

Howrah - 711 322

E : vista@asuranagroup.com ; **W :** www.asuranagroup.com ; **S :** asuranagroup

Ankleshwar Balasor Gangtok Howrah Kolkata